

TEJIDOS REBÉS

BARCELONA
SINCE 1955



Artículo/Article	VIENA TECNOSANI	MASK FFP2 (test itel CE-11339)
REUSABLE (>25 washes)	MADE IN SPAIN	TESTED (ACCORDING UNE-EN14683 and UNE-0065 CEE/93/42)

ANÁLISIS FÍSICO / PHYSICAL ANALYSIS

CARACTERÍSTICAS	RESULTADOS / RESULTS		VALORES / VALUES	TEST		
Nº de Hilo/Thread Count	Urdimbre / Warp	30 1/C				
	Trama / Weft	30 1/C				
Densidad / Density	Urdimbre / Warp	68				
	Trama / Weft	68				
Ligamento / Weave	PLANA / PLAIN					
Comp. Urd./ Comp. Warp	100% COTTON			ISO 1833:2006		
Comp. Tr./ Comp.Weft	100% COTTON					
Total Comp.	100% COTTON		Simple: No tolerancia Compuesta: +/- 3%			
Ancho Final / Final Width	cm	150 - 155	+/-2%	ISO 3932:1976		
Peso / Weight	gr/m ²	120 - 125	+/-5%	ISO 3801:1977		
Resistencia Rotura/ Breakage	(Kgs.)	Urdimbre	pass	kgf	EN-13795	
		Trama	pass	kgf		
Resistencia Abrasion	pass			EN-13795		
Resistencia Desgarro / Tear	Urdimbre/Warp (G)	N/A	Trama / Weft	N/A	EN-13795	
Encogimiento / Shrinkage	°C	60	% Urdimbre	+/- 3	0 - 3 %	NP EN ISO 5077:2008
			% Trama	+/- 3		

SPECIAL MEDICAL TESTS

CARACTERÍSTICAS	RESULTADOS / RESULTS		VALORES / VALUES	TEST
Washing solidity 60°C	5		0-5	UNE EN ISO-05
Pilling	5		0-5	UNE EN ISO 12945-2
Traspirability	< 60 Pa/cm ²			AST1
Aerosol Filtration Efficiency	>94%			UNE EN14683
Particle Filtration Efficiency	>94%			UNE EN14683
Particle Filtration	0,4 micras and >96% efficiency			UNE EN149
Bacterial presence	DRY: PASS	WET: PASS		EN-13795

ANÁLISIS QUÍMICO / CHEMICAL ANALYSIS

CARACTERÍSTICAS	RESULTADOS / RESULTS		VALORES / VALUES	TEST
pH	Conforme/According Oeko-Tex II		4,0 - 7,5	UNI EN ISO 3071/06
Formaldehído	Conforme/According Oeko-Tex II		<16ppm <75ppm	UNE EN ISO 14184-1:1999
Arlaminas	Conforme/According Oeko-Tex II		20 ppm	UNE 2002/61/CE

PROHIBIDOS / FORBIDDEN

Metales Pesados	Conforme/According Oeko-Tex II	Niquel 0,5 Pg/cm ² - Cadmio 75 pm - Plomo 100 ppm
AZO Colorants	Conforme/According Oeko-Tex II	No detectable
Colorantes Alérgicos	Conforme/According Oeko-Tex II	No detectable (LMBG) (1/4/96)

SÍMBOLOS DE LAVADO / WASH CARE SYMBOLS					
--	--	--	--	--	--

Observaciones:
TRAS 25 LAVADOS EL ACABADO EMPIEZA A PERDER PROPIEDADES - LAVAR CON DETERGENTE NEUTRO
AFTER 25 WASHES THE FINISH BEGINS TO LOSE PROPERTIES - WASH WITH NEUTRAL DETERGENT
NO USAR LEJIA / DO NOT USE BLEACHING
PLANCHADO A 140° de 10-15 SEGUNDOS / IRON 140° FOR 10-15 SECONDS
ORGANIC COTTON *GOTS bajo pedido / on request